

■ moglice P500 #0296

Product description

moglice P500 is a medium-viscosity 2-component sliding surface. this is used for the production of guides, hydrostatic guides, sliding bearings and sliding surfaces. The precise moulding technology enables complex shapes and structures without mechanical processing with a precision in the μm range. In modern production technology, process times and costs can be reduced many times over. The material can be detached from the counter surface by using a micro-thin layer of Diamant release agent. The result is an exact copy of the workpiece surface.



Typical applications

- Sliding coverings and guides in mechanical engineering
- Slides for punching sliders with permanent lubrication
- Sliding surfaces for surface air bearings on glass grinding machines
- Slides for transport systems for electronic elements such as waivers, displays or photovoltaics
- Guided guides for positioning at high speeds
- Sliding surfaces in pressure cylinders
- Sliding surfaces in lubrication-free actuators and clutch elements
- Repairs of sliding surfaces

Characteristics

- simple, medium-viscous application by injection technique
- μm -precise molding
- High dimensional stability
- High resistance to cooling emulsions, mineral and synthetic lubricants and cutting agents
- Anti-Sick-Slip Behavior
- Emergency running characteristics
- Excellent load transfer due to complete contact surfaces

Chemical resistance

For questions about chemical resistance please contact our technicians.

Pack sizes

Article

V05 250g

Description

Custom sizes on request.

Product data condition of delivery

Hue component A (resin)	black
Component B (hardener)	clear-yellow
Storability	18 months at 5°C to 20°C
Viscosity	75000 mPas
Mixing ratio	[A : B] (gr) 88:12
Pot life	50 minutes at 20°C
Curing complete	24 hours at 20°C
for deformation	18 hours at 20°C
Processing temperature	10°C to 30°C

Product data outreacted product

Density	1.6 g/cm ³
Compressive strength	110 N/mm ² DIN EN 12190:1998
Strength	87
E-Modul	9500 N/mm ² DIN EN 13412:2006
temperature resistance (permanent)	-20 to +60 °C
temperature resistance (short-term)	-40 to +125 °C
Shrinkage	less than 0,1 % DIN EN 12617-4/2002

Storage / Shelf life

Store in original, unopened container in a dry, cool and frost-free place (+5°C to +20°C). Shelf life 18 months. Protect from direct sunlight. Higher temperatures reduce the shelf life.

Processing the adhesion surface

The guide surface to be coated is roughened to improve adhesion. The peak-to-valley height should be 0.5 mm (Rt-500 µm). The roughening can be produced with a cutter head with a large feed on a milling machine.

Mixing Procedure

To mix moglice P500, add component B completely to the component A container. Mix intensively with a drill and the DIAMANT mixing propeller (Prod. No. #0789) (max. 250 rpm for approx. 2 minutes). Scrape off any material adhering to the wall of the container with a spatula and add to the mixture. Mix again thoroughly.

Ventilate

moglice P500 should be transferred to a clean container in a long, thin, uninterrupted stream.

Description of use

Transfer moglice P500 into a 1K empty cartridge and inject with this through an inlet channel into the prepared, sealed cavity. To avoid the influence of air, fill the cavity from the deepest point.

Qualification and Service

To ensure the best possible quality as well as error-free application, we offer the following services:

- Consultation by phone and/or at your site
- Site supervision and monitoring of the work on site
- Complete execution of the work by our experienced application technicians

Disposal

Unused residual material from the cans can be disposed of normally when mixed in the correct ratio and fully cured (EAKV170203). Unmixed material must be disposed of as chemical waste (EAKV 080111). When booking the Diamant Service Team, waste will be disposed of by us.

Safety data sheet

Please read the corresponding safety data sheet before processing the product. Safety data sheets are available daily on request via info@diamant-polymer.de or by phone at +49-2166-98 360. DIAMANT guarantees the product characteristics as long as they are stored and used according to the specifications listed here. DIAMANT does not assume any responsibility for the processing of the material. Our technicians will be happy to answer any further questions you may have.

Accessories / Processing equipment

#1354 Release agent, liquid#1355 Release agent, spray 500 ml#1417 Cleaner, liquid#1534 Cleaner, spray 500 ml#78 Spatula, DIAMANT green#0789 Mixing propeller#1573 1C empty cartridge 320 ml#1572 1C empty cartridge 160 ml#1574 1C cartridge press (manual) for empty cartridge 320 / 160 ml#1579 PE hose, clear, D= 8 mm#1577 Shut-off valves, D = 8 mm#1578 Screw-in hose nipple R1/4"#7010 Foam rubber sealing tape HxW 10 x 15 mm#1580 Foam rubber sealing tape HxW 4 x 9 mm

Disclaimer

The following supersedes the buyer's documents. Seller makes no express or implied representations or warranties, including merchantability or fitness for a particular purpose. Although the advice and information contained in this publication is based on our own findings and is believed to be reliable, we cannot accept any responsibility for the suitability or results of the processing of the products described herein, nor for any loss or damage caused directly or indirectly by the processing of our products. Before using the described products, the processor is obliged to ensure the quality, safety and other relevant properties by his own tests. We guarantee the flawless quality of our products in accordance with our General Terms and Conditions. The Buyer's sole remedy and the Seller's sole liability for any claims are the Buyer's purchase price. No reference in this document may be construed as an incentive, recommendation or permission to disregard existing intellectual property rights. When handling our products, the industrial hygiene and legal regulations must be observed. For further information, please refer to the relevant safety data sheets. This edition replaces all previous versions